




Maintenance-Free Rechargeable Sealed Lead-Acid Battery




BP10-4

The battery is constructed by plates, separators, safety valves and container. Since the electrolyte is held by a glass-mat separator and plates, the battery can use in any direction and position without leakage.


PERFORMANCE SPECIFICATIONS

Nominal Voltage(V).....	4 volts(2cells in series)
Nominal Capacity(AH)	
20 hour rate F.V.(1.75V/cell) (500mA to 3.50volts)	10A.H.
10 hour rate F.V.(1.75V/cell) (950mA to 3.50volts)	9.5A.H.
5 hour rate F.V.(1.75V/cell)(1700mA to 3.50volts)	8.5A.H.
1 hour rate F.V.(1.55V/cell) (6000mA to 3.10volts).....	6A.H.
Approximate Weight.....	1310g(2.89lbs.)
Terminal	
Standard.....	Type T1
Optional.....	Type T2
Internal Resistance (Fully Charged Battery).....	<8mΩ
Maximum Discharge Current For 5 sec.(A).....	150A
Maximum Charge Current(A).....	3.00A
Ambient Temperature	
Charge.....	0°C(32°F)~40°C(104°F)
Discharge.....	-20°C(-4°F)~50°C(122°F)
Storage.....	-20°C(-4°F)~40°C(104°F)
Vibration test:	
Frequency: 16.7HZ	
Amplitude: 4mm	
Vibrate the battery horizontally or vertically for 60 minutes. The battery have no abnormality.	
Case.....	ABS
Dimension(mm/inch)	
Length ±1.5mm.....	101/3.98
Width ±1.5mm.....	50/1.97
Container Height ±1.5mm.....	94/3.70
Total Height ±2mm.....	100/3.94
Application.....	Lighting, Medical, Old Laptop.

BP10-4 Battery discharge characteristics (25°C/77°F)



BATTERY CHARGING CHARACTERISTICS (Typical example of the charge characteristics for the standby use)




Charging Procedure

Application	Charging method	Charging Voltage at 20°C (V/cell)	Temperature compensation coefficient of charging voltage (mV/°C/cell)	Max. charging current (CA)	Charging time 0.1CA, 20°C (h)		Temp (°C)
					100% discharge	50% discharge	
For standby power Source	Constant voltage & Constant current charging (with current restriction)	2.25 ~ 2.30	-3	0.3	24	20	0-40 (32-104°F)
For cycle service		2.40 ~ 2.50	-4	0.3	16	10	


*Temperature compensation of charging voltage is not needed, when using the batteries within 5°C to 35°C range.

Effect of Temperature on Long Term Float Life



TERMINAL TYPE mm(inch)


OUTER DIMENSIONS



Constant power discharge characteristics at 25°C/77°F

Final Voltage	Discharge time								
	5Min	10Min	15Min	30Min	1Hr	3Hr	5Hr	10Hr	20Hr
3.60V	120.6	88.8	71.1	42.3	24.26	9.71	6.70	3.74	1.96
3.50V	139.5	96.2	74.4	43.9	24.99	9.91	6.80	3.80	2.00
3.40V	148.2	99.6	76.7	44.9	25.44	10.00	6.84	3.82	2.01
3.30V	154.9	102.0	78.4	45.5	25.74	10.07	6.86	3.83	2.01
3.20V	160.0	104.0	80.0	46.0	26.00	10.13	6.88	3.83	2.01

TERMINAL POSITION



B.B. BATTERY CO., LTD. Web Site: <http://www.bb-battery.com>

USA :

B&B BATTERY (USA) INC.
6415 RANDOLPH ST. COMMERCE,
CA, 90040 U.S.A.
TEL: 1-323-278-1900 1-800-278-8599
FAX: 1-323-278-1268

CHINA FACTORY:

CHENG DONG TRIAL AREA, HUANG GANG,
RAOPING GUANG DONG, CHINA, 515700
TEL: 86-768-7601001-2
FAX: 86-768-7601469

UK:

B & B BATTERY (UK) CO., LTD.
TEL: 44-161-339-9458
FAX: 44-161-343-7030

HONG KONG:

NATIONAL TRADING LTD.
TEL: 852-2301-3800
FAX: 852-2739-1182

JAPAN:

B & B BATTERY (JAPAN) CO., LTD.
TEL: 81-426-256-537
FAX: 81-426-256-537

TAIWAN:

B & B BATTERY CO., LTD.
TEL: 886-6-5898081-3
FAX: 886-6-5898087



MH19884



ISO 9001



QUALITY ASSURED FIRM



NATIONAL ACCREDITATION OF CERTIFICATION BODIES



Reg. No. 059-C